

H6906 PermaStripe Smooth Data Sheet

Subject	Result	Test Method
Plastic composition	PVC	N/A
Plastic thickness	1mm	N/A
Peel adhesion N/25mm	42.2	180° FINAT FTMI
Tensile strength, N/25mm	>200	Lloyd 500N load cell
Adhesive thickness	0.2mm	N/A
Total thickness	1.3mm	N/A
Initial tack (cm)	< 8	PSTC-6
180° Adhesion (kg/25.4mm)	>1.8	ASTM-D1000
Holding Power (hrs/kg/25.4mm ²)	>48	PSTC-7
Temperature range	-30°C to +70°C	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England.

LRV Test Results

SKU (Colour)	RAL	Pantone	Av. LRV	Range
H6906N (Black)	9004	Black 6 U	3.4	0.4
H6906R (Red)	3018	199 U	19.9	0.4
H6906O (Orange)	2008	021 U	36.2	0.6
H6906Y (Yellow)	1018	108 U	64.6	2.9
H6906V (Green)	6018	Green U	30.1	1
H6906B (Blue)	5012	281 U	21	1.1
H6906W (White)	9003	7541 U	88.5	10.1
H6906D (Black/ Yellow Hazard)	9004 / 1021	Black 6 U / 1235 U	3 / 61.8	0.5 / 0.5
H6906A (Red/ White Hazard)	3001 / 9003	485 U / 7541	1.1 / 77.4	1.1 / 1.2

All the above data is for reference only.

©Heskins Ltd 1997-2024

